

## PRODUCT DATA SHEET

# Purolite® NRW3560

Polystyrenic Macroporous, Gel,  
Mixed Bed Resin, Hydrogen form,  
Hydroxide form, Nuclear Grade

## PRINCIPAL APPLICATIONS

- Primary purification
- Demineralization - Steam Generator  
Blowdown

## TYPICAL PACKAGING

- 1 CF Box
- 5 ft<sup>3</sup> Drum (Fiber)

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical Beads	
Particle Size Range	425 - 1200 µm	
< 425 µm (max.)	2 %	
Uniformity Coefficient (max.)	1.7	
Impurities Iron (max.)	50 ppm	
Impurities Sodium (max.)	30 ppm	
Impurities Heavy Metals (max.)	40 ppm	
Anionic Form, CO <sub>3</sub> <sup>2-</sup> (max.)	5 %	
Anionic Form, SO <sub>4</sub> <sup>2-</sup> (max.)	0.1 %	
Anionic Form, Cl <sup>-</sup> (max.)	0.1 %	
Specific Gravity	1.08	
Shipping Weight (approx.)	720 - 750 g/L (45.0 - 46.9 lb/ft <sup>3</sup> )	
Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F)	
Temperature Limit, Regenerable Bed	60 °C (140.0 °F)	
Component Name	Macroporous Strong Acid Cation	Gel Strong Base Anion
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H <sup>+</sup> form	OH <sup>-</sup> form
Cation / Anion Chemical Equivalent Ratio	1	1



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com

Total Capacity (min.)	2.1 eq/L (H <sup>+</sup> form)	1.1 eq/L (OH <sup>-</sup> form)
Conversion (min.)	99.9 % (H <sup>+</sup> form)	95 % (OH <sup>-</sup> form)
Specific Gravity	1.21	1.08



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com