

## PRODUCT DATA SHEET

# Puromet™ MTS9300

Polystyrenic Macroporous,  
Iminodiacetic acid Chelating Resin,  
High Capacity

## PRINCIPAL APPLICATIONS

- Copper Removal
- Cobalt Removal
- Nickel Removal
- Zinc Removal
- Wastewater Treatment

## ADVANTAGES

- High operating capacity
- Excellent osmotic stability

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Iminodiacetic
Ionic Form	Na <sup>+</sup> form
Copper Capacity (min.)	50 g/L
Moisture Retention	52 - 60 % (Na <sup>+</sup> form)
Particle Size Range	425 - 1000 µm
< 425 µm (max.)	2 %
Uniformity Coefficient (max.)	1.5
Reversible Swelling, H <sup>+</sup> → Na <sup>+</sup> (max.)	35 %
Specific Gravity	1.18
Shipping Weight (approx.)	750 - 800 g/L (46.9 - 50.0 lb/ft <sup>3</sup> )
Temperature Limit	80 °C (176.0 °F)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com