

## PRODUCT DATA SHEET

# Purolite® A400DL

Polystyrenic Gel, Type I Strong  
Base Anion Resin, Chloride form,  
Layered Bed grade

### PRINCIPAL APPLICATIONS

- Demineralization - Industrial
- Silica Removal

### ADVANTAGES

- High operating capacity
- Efficient regeneration

### SYSTEMS

- Layered Beds

### REGULATORY APPROVALS

- IFANCA Halal Certified
- LPPOM MUI Halal Certified

### TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

### TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	Cl <sup>-</sup>
Total Capacity	1.3 eq/L (28.4 Kgr/ft <sup>3</sup> ) (Cl <sup>-</sup> form)
Moisture Retention	48 - 54 % (Cl <sup>-</sup> form)
Particle Size Range	630 - 1200 µm
< 630 µm (max.)	5 %
Uniformity Coefficient (max.)	1.4
Reversible Swelling, Cl <sup>-</sup> → OH <sup>-</sup> (max.)	20 %
Specific Gravity	1.08
Shipping Weight (approx.)	680 - 700 g/L (42.5 - 43.8 lb/ft <sup>3</sup> )
Temperature Limit	100 °C (212.0 °F) (Cl <sup>-</sup> form)
Temperature Limit	60 °C (140.0 °F) (OH <sup>-</sup> form)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com