

PRODUCT DATA SHEET

Puromet™ MTS9500

Polystyrenic Macroporous,
Aminophosphonic Chelating Resin

PRINCIPAL APPLICATIONS

- Iron Removal
- Copper Removal
- Zinc Removal
- Antimony Removal
- Bismuth Removal

ADVANTAGES

- Highly selective

SYSTEMS

- Acidic liquors and pulps

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Aminophosphonic
Ionic Form	Na ⁺ form
Calcium Capacity (min.)	26 g/L
Moisture Retention	60 - 68 % (Na ⁺ form)
Particle Size Range	300 - 1200 µm
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Reversible Swelling, H ⁺ → Na ⁺ (max.)	50 %
Specific Gravity	1.13
Shipping Weight (approx.)	710 - 760 g/L (44.4 - 47.5 lb/ft ³)
Temperature Limit	80 °C (176.0 °F)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com